

THE DUPLEX-TIGRAL® BENEFIT




voestalpine eifeler Coatings developed this high performance Physical Vapour Deposition coating for very high resistance against oxidation and abrasion. This two stage process is comprised of a specially developed Plasma Nitride followed by a mono-layered matrix coating. Duplex-TIGRAL was created to eliminate the drawbacks associated with high temperature coatings like Thermoreactive Diffusion and Chemical Vapour Deposition. Duplex-TIGRAL will easily match the performance levels of these hot treatments. Additionally, Tigral can be stripped and recoated multiple times.

BENEFITS OF DUPLEX-TIGRAL:

- » Increased Tool Life
- » Lower Tool Maintenance
- » Reduced Down Time
- » Higher Productivity
- » Improved Part Quality





The unique chemistry of Duplex-TIGRAL offers protection from materials that corrosively attack the tool steel. This results in reduced adhesive wear and alloying between work material and tool steel which results in enhanced part release and greater productivity.

- » High Hardness and Wear Resistance
- » Superior Abrasion and Erosion Resistance
- » Corrosion Resistance from Alloying Attack
- » High Oxidation Temperature and Thermal Stability
- » Improved Coefficient of Friction



APPLICATIONS

Duplex-TIGRAL clearly provides performance improvements to tools in the most severe applications. Increased tooling life and reduced maintenance costs have been demonstrated in the following applications:

- » High Pressure Aluminum Die Casting
- » Forming of Abrasive Stainless Steel and Ferrous Alloys
- » Hot and Cold Forging
- » Hot Stamping
- » Non Ferrous Extrusion

Duplex-TIGRAL offers excellent adhesion and performance on all common and advanced tool steels including welded substrates. It can be applied to:

- » UDDEHOLM Orvar® Supreme and Orvar® Superior
- » BÖHLER W403 VMR®
- » BÖHLER W400 VMR®
- » UDDEHOLM Dievar®
- » BÖHLER W360 ISOBLOC®
- » H13, H11 and other hot work tool steel
- » UDDEHOLM Caldie®
- » BÖHLER K340 ECOSTAR®/ISODUR® (8 percent Chromium tool steel)
- » High Temperature Tempered D2 and other cold work tool steels

TIGRAL: ADDITIONAL APPLICATIONS

TIGRAL can also be applied using a non-duplex process. Applications include coated cutting tools for dry machining, and tools that machine at high feed rates - ideal for tools that specialize in interrupted cuts. TIGRAL can also be used in the reaming of medium and highly alloyed steels. Additionally, it can be used in warm and cold forming, and hot stamping processes where high ductility and low tendency to cold weld to the steel are required.

PROPERTIES

Material: Aluminum Chromium Titanium Nitride

Micro-hardness HV 0.05: 3300 ± 300

Coefficient of friction: 0.6 Layer thickness: 3-5 µm

Maximum service temperature: 900°C/1650°F

Color: Dark Grey

Plasma nitriding with zero white layer

Process temperature: 500°C/925°F) maximum

(with Duplex process)





Locations:

Canada - voestalpine eifeler Coatings voestalpine High Performance Metals Ltd.

2645 Meadowvale Blvd. Mississauga, ON L5N 7Y4 T. +1 (800) 665-8335 F. +1 (905) 812-9231

Email: sales.canada@voestalpine.com

USA - voestalpine High Performance Metals LLC

voestalpine eifeler Coatings LLC - Illinois

Headquarters 2475 Millennium Drive Elgin, IL 60124 T. +1 (630) 587-1220

Email: sales.usa@eifeler.com

voestalpine eifeler Coatings LLC - California

EDRO Engineering LLC 20492 Carrey Road Walnut, CA 91789 T. +1 (909) 594-5751 Email: coatings@edro.com

voestalpine eifeler Coatings LLC - Michigan

2222 Spikes Lane Lansing, MI 48906 T. +1 (517) 708-7945 F. +1 (517) 913-6279 Email: sales.usa@eifeler.com

Lindii. 3dies.dsd@eiieiei.com

voestalpine eifeler Coatings LLC - Mississippi

11175 MS 178 Olive Branch, MS 38654 T. +1 (662) 932-8094 Email: sales.usa@eifeler.com

voestalpine eifeler Coatings LLC - Ohio

18687B Sheldon Road Middleburg Heights, OH 44130 T. +1 (216) 658-3870 F. +1 (216) 658-3871

Email: sales.usa@eifeler.com

voestalpine eifeler Coatings LLC - Tennessee

3450 Old Tasso Road NE Cleveland, TN 37312 T. +1 (423) 790-7382 F. +1 (423) 790-7386

Email: sales.usa@eifeler.com

Mexico - voestalpine eifeler Coatings voestalpine High Performance Metals S.A. de C.V.

voestalpine eifeler Coatings - Querétaro

Cerrada de la Noria No. 200 Int. A-14 Parque Industrial Querétaro, C.P. 76220. Querétaro, México T. +52 (442) 689-5900 +52 (442) 689-5901

Email: ventas.mexico@voestalpine.com

voestalpine eifeler Coatings - Monterrey

Blvd. Milenium No. 5052
Parque Industrial Milenium Aeropuerto, C.P. 66626
Apodaca, Nuevo León, Monterrey
T. +52 (81) 8352-5239
Email: ventas.mexico@voestalpine.com

www.eifeler.com/northamerica

